



6400 Shawson Drive, Unit 1, Mississauga, ON L5T 1L8
 Tel: (905) 564-0807 Fax: (905) 564-4812

STYLE 7330
Braided Packing
Kevlar® Yarn,
PTFE Impregnated

CONSTRUCTION

Style 7330 is an interlock braided packing using Kevlar® yarn treated with PTFE suspenoid. The packing is also lubricated with mineral oil for quick and easy break-in.

APPLICATION / SERVICE

Style 7330 is an extremely durable packing able to withstand granular and abrasive applications. It is recommended for service in steam, slurries, petroleum derivatives, solvents and liquified gases. It is commonly used in centrifugal, rotary and reciprocating pumps, agitators and mixers, especially in the paper, steel, petroleum and chemical industries, and in sewage treatment plants.

SERVICE LIMITS

Temperature:

Minimum -150°F (-100°C)
 Maximum 540°F (280°C)

Pressure:

Rotating 500 psi (35 bar)
 Reciprocating 2900 psi (200 bar)
 Static 3600 psi (250 bar)

Shaft Speed: 2950 fpm (15 m/s)

pH Range: 2 - 12

APPROXIMATE YIELDS - FEET PER POUND

1/8"	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
74.4	33.8	25.7	16.9	11.9	9.0	6.6	5.6	4.2	3.0	2.4	1.7

** Kevlar is a registered trademark of E.I. du Pont de Nemours & Co., (Inc.)*

Properties and application parameters shown are typical and are presented in good faith but no warranty is expressed or implied. This edition supersedes all previous issues and all data is subject to change without notice.
 11/96