



6400 Shawson Drive, Unit 1, Mississauga, ON L5T 1L8
Tel: (905) 564-0807 Fax: (905) 564-4812

Gasket Sheet

Style

**Pure Gum Rubber
40 Duro**

**PURE GUM RUBBER 40 DUROMETER
ISO/ASTM DESIGNATION = NR**

Physical Characteristics:

Tensile: 2320 PSI

Elongation: 600%

Hardness: 40 SHORE "A" +/-5

Temperature Range: -40°F to 158°F (-40°C to 70°C)

NOTE: A soft, long wearing non-marking natural rubber. Pure gums have excellent abrasion and tear resistance. It also has superior resilience, tensile and elongation characteristics. Gum rubber is also excellent on all steel surfaces against abrasion. Pure gum is not suitable for outdoor or oil resistance applications. It is also used for gasket and sand/shot blast curtain manufacturing. Pure Gum Rubber has excellent adhesion to fabric and metal. It is widely used to manufacture sleeves for chutes on cement mixers.