



6400 Shawson Drive, Unit 1, Mississauga, ON L5T 1L8
Tel: (905) 564-0807 Fax: (905) 564-4812

Gasket Sheet

Style

**Flexible Graphite
316 SS Tang Insert**

Product Description:

Laminated Graphite Sheets with reinforcement .004" thick perforated 316 stainless steel tang insert, mechanically bond. Made from Flexible Graphite Industrial Grade (99% carbon)

Main Characteristics

Excellent Sealability that meets stringent emission regulations
High Temperature Resistant
Chemical Resistant
Blow-out Resistant
Non-aging, no creep relaxation
Meets most industrial fluid sealing service requirements (Recommended for 150 and 300 class service)

Chemical Compositions of Flexible Graphite

Carbon: 99% Min.; Ash: 0.8% Max; Leachable Chloride: 30ppm Max

Typical Physical Properties

M Factor: 2 (Smooth Flange Surface)
Y Stress: 2500 psi (17 MPa) (Smooth Flange Surface)

Gasket Constants per ASME:

Gb	1400 psi	(9.65 N/mm ²)
A	0.324	
Gs	0.01 psi	(6.9x10 ⁻⁵ N/mm ²)

Creep Relaxation (ASTM F-38) Less than 5%

Working Temperature Range:

Oxidizing Environment, such as air: -400° F to 950° F (-240°C to 510°C)
Mild Oxidizing Environment of most gasket applications: -400° F to 1500° F (-240°C to 850° C)
Non-oxidizing Environment: Up to 1800° F, the limit of Stainless Steel Insert (Limit of Graphite is 5400° F)

Applications

This Material is an ideal sheet gasket material for most industrial fluid sealing applications. It is resistant to corrosive chemicals, high temperature, and high pressure. Can be used in refineries, chemical and petrochemical plants, paper mills, mines and other industrial fields.

Standard Sizes

Thickness: 1/32", 1/16", 1/8"
Sheet Size: 39.4" x 39.4" (Meter Size), 60" x 60" nominal (59.1" x 59.1" or 1.5m x 1.5m)